


CENTURY Grey Back



Substance g/m ²	Thickness micron	Bulk cc/gm	L & W Bending Resistance, mN		
			MD	CD	GM
T 410	T 411		T 556		
200	245	1.23	81	42	58
220	270	1.23	105	52	74
230	282	1.23	125	62	88
250	313	1.25	164	82	116
270	338	1.25	185	95	133
280	355	1.27	195	100	140
290	372	1.28	215	110	154
296	380	1.28	230	118	165
300	385	1.28	265	135	189
320	415	1.30	325	164	231
330	428	1.30	355	179	252
340	442	1.30	380	192	270
350	455	1.30	410	207	291
370	485	1.31	470	235	332
400	525	1.31	570	292	408
420	555	1.32	625	320	447
430	568	1.32	675	345	483
450	595	1.32	715	365	511
470	635	1.35	760	390	544
Tolerance : ± 3%		± 4%	± 15%		

Properties		UOM	Value	Standards
Roughness (PPS) Top	<350 gsm	μ	2.0 Max	T 555
	>350 gsm		2.5 Max	
IGT Dry Pick (MV)	Top	m/s	1.2 Min	ISO 3782
Gloss at 75°, min	Top	%	35 min	T 480
ISO Brightness	Top	%	80 ± 2	ISO 2470
Scott Ply Bond		j/m ²	120 min	T 569
Cobb ₆₀	Top	g/m ²	35 ± 10	T 441
	Back		50 ± 10	
Moisture	< 230	%	5.0 - 7.0	T 412
	230 - 350		6.0 - 8.0	
	> 350		7.0 - 9.0	
Shade		-	Bluish	As per Standard



CERTIFICATIONS & COMPLIANCES:
Manufacturing: ISO 9001, ISO 14001, OHSAS 18001 and FDA
Regulatory: REACH & ROHS

NOTE:
Test Conditions: Temperature 23 ± 1°C & Relative Humidity 50 ± 2%. (Tappi 402)
All Parameters are measured as per the relevant Tappi & ISO standards.

Being a dynamic organization, Century Pulp & Paper continuously evolving in response to customer requirement. The specification in this product catalogue are therefore subject to change. To learn more about our upgraded specification sheet contact: cppdel@centurypaper.org.in