


Substance g/m ²	Thickness micron	Bulk cc/gm	L & W Bending Resistance, mN		
			MD	CD	GM
T 410	T 411		T 556		
200	265	1.33	88	44	62
210	280	1.33	105	53	74
220	292	1.33	125	62	88
230	305	1.33	140	70	99
250	335	1.34	178	90	127
270	362	1.34	225	115	161
280	380	1.36	250	125	177
290	395	1.36	280	145	201
300	410	1.37	310	168	228
320	445	1.39	400	216	294
330	460	1.39	430	232	316
340	475	1.40	470	254	346
350	490	1.40	520	289	388
Tolerance: ± 3%	± 4%		±15%		

Properties		UOM	Value	Standards
Roughness (PPS) Top	200-300 gsm	μ	1.8 max	T 555
	> 301 gsm		2.0 max	
IGT Dry Pick (MV)	Top	m/s	1.2 ± 0.2	ISO 3782
Gloss at 75°, min	Top	%	38	T 480
ISO Brightness	Top	%	85 ± 2	ISO 2470
Scott Ply Bond		j/m ²	>130	T 569
Cobb ₆₀	Top	g/m ²	30 ± 5	T 441
	Back		50 ± 5	
Moisture	<250	%	6.0 - 7.0	T 412
	251 - 300		6.5 - 7.5	
	>301		7.0 - 8.0	
Shade		-	Light Bluish	As per Standard



CERTIFICATIONS & COMPLIANCES:
Manufacturing: ISO 9001, ISO 14001, OHSAS 18001 and FDA
Environmental: FSC COC and ECF.
Regulatory: REACH & ROHS

NOTE:
Test Conditions: Temperature 23 ± 1°C & Relative Humidity 50 ± 2%. (Tappi 402)
All Parameters are measured as per the relevant Tappi & ISO standards.

Being a dynamic organization, Century Pulp & Paper continuously evolving in response to customer requirement. The specification in this product catalogue are therefore subject to change. To learn more about our upgraded specification sheet contact: cppdel@centurypaper.org.in